
DATASHEET

SIREX[®] PE30

ismt



BENEFITS

- Completely closed cell
- Fine, regular cell structur
- Good mechanical properties
- Excellent thermal insulating
- Permanently elastic
- Minimal water absorption
- Very low water vapour permeability
- Good resistant to most chemicals
- Permanently resilient
- Environmentally friendly
- Non-toxic
- Does not contain CFCs
- Good adhesion

SIREX PE30

SIREX PE30 is a closed-cell chemical cross-linked PE foam with a density of approx. 33 kg/m³. Standard size of a base block is approx. 2000 x 1000 x 110 mm.

PROCESSES AND APPLICATIONS

SIREX PE30 is available in the desired thickness and shape. For example, the following processing techniques can be applied to the material: skiving, laminating, cutting, punching, milling, water-jetting, laser, butt welding, self-adhesive and thermoforming.

Some applications of the SIREX PE30 are:

Industrial gaskets, insulation, boat fenders, (presentation) packaging, cutting – punching parts and water play equipment.



ISMT B.V. Küppersweg 18 NL - 2031 EC Haarlem



Niederlassung Deutschland Ludwig-Herr-Str. 23 D - 70806 Kornwestheim



+31 (0)88 018 4900 +49 (0)7154 3091



www.ismt-bv.com sales@ismt-bv.com



ir documentation, product information, recommendations and price lists have been compiled the best of our knowledge and ability, and are based on average values and data known at the ne of writing. They are not legally binding in any way





DATASHEET SIREX[®] PE30

TECHNICAL INFORMATION

PROPERTIES	NORM	UNIT	VALUE
Thickness	IE-03	mm	110 ± 5
Length	IE-03	mm	≥ 2000
Width	IE-03	mm	≥ 1000
Density	IE-04	kg/m ³	33 ± 4
Cell size	IE-09	mm	0,24
Elongation at break	IE-06	%	116
Tensile Strength	IE-06	kPa	189
Compression strength	IE-05		
10% compression		kPa	42
25% compression		kPa	55
50% compression		kPa	107
Compression Set, 25%, 22 h	IE-07		
0,5 h recovery		%	11
24 h recovery		%	4
Shore hardness	IE-08	∞	≥49
Water Absorption (28 days)	DIN 53428		
vol% water absorption		%	1
Maximum working temperature	IE-02	°C	100
Thermal conductivity	ISO 2581		
at 10 °C		W/mK	0,036
at 40 °C		W/mK	0,038
Flammability thickness 10 mm	ISO 3795	mm/min	≤ 100

The internal norms IE-03, IE-04, IE-05, IE-06 and IE -07 are based by standards ISO 1923, ISO 845, ISO 844, ISO 1926 and ISO 1856-B, respectively.



Our documentation, product information, recommendations and price lists have been compiled to the best of our knowledge and ability, and are based on average values and data known at the time of writing. They are not legally binding in any way

