



BENEFITS

- Fully closed cell
- Fine, regular cell structure
- Good mechanical properties
- Excellent thermal insulation
- Minimal water absorption
- Very low water vapour permeability
- Chemically inert, good resistance to most chemicals
- Environmentally friendly
- Non-toxic
- Does not contain CFCs

SIREX BLOCK P59

SIREX® BLOCK P59 is a fine-celled, physically crosslinked PE foam. SIREX® BLOCK P59 has a very fine and uniform cell structure. SIREX® BLOCK P59 is chemically inert, odourless, environmentally friendly, recyclable and free from harmful chemical additives. SIREX® BLOCK P59 is delivered in blocks and is on demand also available in sheets at desired thickness, strips, with self-adhesive and much more. Don't hesitate to contact us for additional information regarding the possibilities.



ISMT B.V.
Küppersweg 18
NL - 2031 EC Haarlem



Niederlassung Deutschland
Ludwig-Herr-Str. 23
D - 70806 Kornwestheim



+31 (0)88 018 4900
+49 (0)7154 3091



www.ismt-bv.com
sales@ismt-bv.com

TECHNICAL INFORMATION

PROPERTIES	STATUS	NORM	UNIT	AVERAGE	MIN	MAX
General						
thickness	**	ISO-1923	mm		- 0	
apparent density	**	ISO-845	kg/m ³	60	54	66
Compression Stress/Strain, S						
deflection 25%	F	ISO-3386-1	kPa	150	100	200
deflection 40%	F		kPa	190	130	250
deflection 50%	F		kPa	240	170	310
Compression Set 25%						
deflection 25%, ½ h after discharge	F	ISO-1856-C	%	9	6	12
deflection 25%, 24 h after discharge	F		%	4	3	5
Thermal Stability						
max. temperature dimensional change, lengthwise and crosswise	F	Internal	°C	max. 110		
	F		%	< -5		
Water Absorption						
vol. % water absorption	F	ISO-2896	vol%	<1		

All properties are based on individual values and should be considered as guideline, not as specification.

** : to be considered as specification

P : to be considered as provisional property

F : to be considered as final property